


## Designed to enhance safety by offering extra durability

- Three times thicker than standard latex gloves to prevent rips, snags and tears
- Soft, elastic fit and feel
- Textured fingers for reliable grip
- Extended cuff for expanded protection over the wrist and forearm
- Double chlorinated for easy donning
- Meets or exceeds the emergency medical glove requirements of NFPA 1999



### Industries

- Automotive
- Automotive Aftermarket
- Life sciences
- Healthcare

### Recommended For

- Inspection, selecting, checking parts
- Assembly and inspection of components
- Picking and fastening components
- Equipment repair and maintenance
- General Purpose Auto Aftermarket
- Body panel repair and replacement
- Tire rotation & changes
- Animal care feeding and cleanup
- Maintaining lab furniture and equipment
- Sample taking and processing
- Raw material sample collection
- Extra protection over the wrist and arm
- Higher-risk clinical applications
- Tested for use with chemotherapy drugs



### TECHNICAL DATA SHEET

#### PRODUCT INFORMATION

SafeGrip® SG-375	
<b>Material</b>	Natural Rubber Latex
<b>Color</b>	Blue
<b>Glove Design</b>	Chlorinated, Powder-Free, Textured Fingers
<b>Cuff</b>	Beaded
<b>Manufacturing/QMS Audit Standards</b>	EN ISO 13485 : 2012
<b>Regulatory/Standards Compliance</b>	ASTM D3578, Food Contact, US QSR/FDA 510(k) Medical Examination Grade
<b>Packaging</b>	50 gloves per dispenser 10 dispensers per case 500 gloves per case
<b>Storage</b>	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition
<b>Country of Origin</b>	Malaysia
<b>User Needs Segment</b>	High Risk
<b>Available sizes</b>	S (6.5 - 7), M (7.5 - 8), L (8.5 - 9), XL (9.5 - 10)

#### PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	295 / 11.6		ASTM D3767,EN420
Freedom from Holes (Inspection level I)	1.5 AQL		ASTM D5151
Palm Thickness (mm/inches)	0.28 / 11		ASTM D3767,EN420
Finger Thickness (mm/inches)	0.36 / 14.2		ASTM D3767,EN420
	<b>BEFORE AGING</b>	<b>AFTER AGING</b>	
Ultimate Tensile Strength (MPa)	≥ 34	≥ 21	ASTM D412
Elongation at Break (%)	≥ 850	≥ 750	ASTM D412
Force at break (N)	≥ 15	≥ 10	EN 455-2

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

#### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
Rivers de Business Park  
Blvd Internat onal, 55  
1070 Brussels, Belgium  
T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

#### Asia Pacific Region

Ansell Global Trading Center  
(Malaysia) Sdn Bhd  
Prima 6, Prima Avenue  
Block 3512, Jalan Teknokrat 6  
63000 Cyberjaya  
Selangor, Malaysia  
T: +603 8310 6688  
F: +603 8310 6699

#### North America Region

Ansell Healthcare Products LLC  
111 Wood Avenue South,  
Suite 210  
Iselin, NJ 08830, USA  
T: +1 800 800 0444  
F: +1 800 800 0445

#### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
Blvd. Bernardo Quintana No. 7001-C,  
Q7001 Torre II,  
Suites 1304, 1305 y 1306,  
Col. Centro Sur, c.p. 76079  
Queretaro, Qro. Mex co  
T: +52 442 248 1544 / 248 3133

#### Australia

Ansell Limited  
Level 3,678 Victoria Street,  
Richmond, Vic, 3121  
Australia  
T: +61 1800 337 041  
F: +61 1800 803 578

#### Russia

Ahcenn PYC  
123610 Poccnr, Mockba  
Kpachonpechehckar  
Ha6. 12, n.3, op. 1304A  
Ten. +7 495 258 13 16

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2018 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.